

## Classifications

EN 14700	DIN 8555
T Fe7	UP 5-GF-45-C

## Characteristics

Alloy depositing a ferritic-martensitic steel designed to resist metal-to-metal wear, corrosion and thermal fatigue.

Microstructure:	Martensite + 10 % Ferrite
Machinability:	Good with metallic carbide tipped tools
Oxy-acetylene cutting:	Cannot be flame cut
Deposit thickness:	Depends upon application and procedure used
Welding flux:	Record SA, Record SK

## Field of use

Continuous casting rollers.

## Typical analysis in %

C	Mn	Si	Cr	Ni	Mo	Nb	V	Fe
0.08	0.9	0.4	13.5	2.1	1.1	0.2	0.3	balance

## Typical mechanical properties

Hardness as welded: 42 HRC

## Recommended welding parameters

Wire diameter [mm]	Amperage [A]	Voltage [V]	Stick-Out [mm]	Flux-Rate [kg per kg wire]	Travel Speed [cm/min]
3.2	325 – 500	28 – 32	30 – 35	1.1	40 – 50