

## Classifications

| EN ISO 14341-A  | EN ISO 14341-B | AWS A5.18 / SFA-5.18 |
|-----------------|----------------|----------------------|
| G 46 4 M21 4Si1 | G 55A 4 M21 S6 | ER70S-6              |
| G 46 2 C1 4Si1  | G 55A 2 C1 S6  |                      |

## Characteristics and typical fields of application

Pipeshield X series of solid wires for GMAW are specifically designed for fully automatic circumferential all position pipe welding. Pipeshield X combines the benefits of engineered wire surfaces and thoroughly controlled chemical compositions leading to good impact values even at low temperatures. Consistent wire geometry supports wire feeding and stable arc performance. Pipeshield X 70 covers pipe steel grades up to API X70 offering good impact toughness at low temperatures down to -40 °C (-40 °F) and CTOD values at -10 °C (14 °F). Root pass capability up to X80. This product can be used in sour gas applications. (HIC tested acc. to NACE TM-0284).

## Base materials

API 5L: Grade B, X42, X52, X56, X60, X65 and X70, EN 10208-2: L245MB – L485MB; L245NB – L415NB and similar steel grades

## Typical analysis

|       | C     | Si   | Mn   | S       | P       |
|-------|-------|------|------|---------|---------|
| wt.-% | 0.069 | 0.95 | 1.65 | ≤ 0.015 | ≤ 0.020 |

## Mechanical properties of all-weld metal - typical values (min. values)

| Condition | Yield strength R <sub>p0.2</sub> | Yield strength R <sub>e</sub> | Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) | Impact energy ISO-V KV J |            |
|-----------|----------------------------------|-------------------------------|---|--------------------------|------------|
|           | MPa                              | MPa                           | %   | -20°C J                  | -40°C J    |
| u1        | 485 (≥ 460)                      | 595 (≥ 570)                   | 25 (≥ 18)                                       | 120 (≥ 50)               | 60 (≥ 47)  |
| u2        | 530 (≥ 480)                      | 615 (≥ 580)                   | 24 (≥ 18)                                       | 140 (≥ 75)               | 115 (≥ 47) |
| u3        | 650                              | 715                           | 22  | 170                      | 145        |

u1 untreated, as welded – shielding gas 100 % CO<sub>2</sub>

u2 untreated, as welded – shielding gas Ar + 15 – 25 % CO<sub>2</sub>

u3 untreated, as welded – shielding gas M21, field result, round tensile specimen, longitudinal

## Operating data

|   |                                     |     |                     |
|---|-------------------------------------|-----|---------------------|
|  | <b>Polarity</b>                     | DC+ | <b>Dimension mm</b> |
|   | <b>Shielding gas (EN ISO 14175)</b> | C1  | 1.0                 |
|   |                                     | M2  | 1.02                |
|   |                                     |     | 1.2                 |

## Approvals

TÜV (19421), CE