

Classifications

| | |
|-----------------------|---------------------------|
| EN ISO 14343-A | AWS A5.9 / SFA-5.9 |
| W 19 9 L | ER308L |

Characteristics and typical fields of application

TIG rod of W 19 9 L / ER308L type for welding 1.4306 / 304L, 304LN steel grades. Controlled weld metal ferrite content, 3 – 8 FN (stricter on demand), particularly for good cryogenic toughness and lateral expansion down to –196°C. Max. service temperature 350°C.

Base materials

1.4301 X5CrNi18-10, 1.4306 X2CrNi19-11, 1.4307 X2CrNi18-9, 1.4311 X2CrNiN18-9, 1.4312 GX10CrNi18-8, 1.4541 X6CrNiTi18-10, 1.4546 X5CrNiNb18-10, 1.4550 X6CrNiNb18-10
UNS S30400, S30403, S30453, S32100, S34700
AISI 304, 304L, 304LN, 302, 321, 347

Typical analysis

| | C | Si | Mn | Cr | Ni | FN |
|-------|------|-----|-----|----|------|-------|
| wt.-% | 0.02 | 0.5 | 1.8 | 20 | 10.0 | 3 – 8 |

Mechanical properties of all-weld metal - typical values (min. values)

| Condition | Yield strength | Tensile strength | Elongation A | Impact energy ISO-V KV J | | Lateral expansion |
|-----------|-------------------|------------------|------------------------------------|--------------------------|-----------|-------------------|
| | R _{p0.2} | R _m | (L ₀ =5d ₀) | 20°C | –196°C | mm |
| | MPa | MPa | % | | | –196°C |
| u | 430 (≥ 320) | 550 (≥ 510) | 38 (≥ 25) | 150 (≥ 100) | 65 (≥ 32) | ≥ 0.38 |

u untreated, as-welded – shielding gas Ar

Operating data

| | | | |
|--|-------------------------------------|-------------------|---------------------|
|  | Polarity | DC- | Dimension mm |
| | Shielding gas (EN ISO 14175) | I1 | 1.6 × 1000 |
| | Rod marking | W 19 9 L / ER308L | 2.0 × 1000 |
| | | | 2.4 × 1000 |
| | | | 3.2 × 1000 |

Heat input max. 1.5 kJ/mm, interpass temperature max. 100°C.

Approvals

-