

## Union S 3 NiMo

SAW wire, low-alloyed, cryogenic

Classification	IS							
AWS A5.23 / SFA-5.23				EN ISO 14171-A				
EG				S3Ni1,5Mo				
Characteristi	cs and typical f	fields of applic	ation					
	is a coppered solic with PWHT like no		ged arc weldi	ng of stel grad	es with higher stren	gth and toughness.	. Especially suited	
Typical analysis								
	С	Si	Mn	Ni	Мо	S	Р	
wt%	0.09	0.10	1.60	1.50	0.45	≤ 0.012	≤ 0.012	
Operating data								
				Dimension n	mension mm			
				3.0				
				4.0				
Recommended UV 418 TT UV 420 TT UV 421 TT	UV 420 TTR							
Approvals								
-								