

SAW wire, unalloyed

Classifications						
AWS A5.17 / SFA-5.17				EN ISO 14171-A		
EM12				S2		
Characteristics and typical fields of application						
Union S 2 is a coppered solid wire for submerged arc welding of general structural steel grades up to S235-S420						
Recommended SAW flux:						
UV 305	UV 306	UV 310 P				
	UV 418 TT	UV 420 TT				
UV 422 TT-LH						
Typical analysis						
	С		Si		Mn	
wt%	0.1		0.07		1.1	
Operating data						
		1	Dimension mm			
			•	1.6		
				2.0		
				2.5		
			3	3.0		
			3	3.2		
			4	1.0		
Approvals						
-						