



SAW wire, low-alloyed

Classifications

AWS A5.23 / SFA-5.23 EN ISO 14171-A

EA3 S4Mo

Characteristics and typical fields of application

Union S 4 Mo is a coppered solid wire for submerged arc welding of creep resistant 0,5%Mo steel grades (16Mo3); also 2-run procedures in unalloyed steel grades (e.g pipe manufacturing).

Typical analysis

	C	Si	Mn	Мо
wt%	0.11	0.10	2.00	0.50

Operating data

Dimension mm

4.0

4.8

Recommended SAW flux:

UV 309 P

UV 310 P UV 420 TT-LH UV 418 TT UV 420 TTR

Approvals

_