

## Classifications

<b>EN ISO 14343-A</b>	<b>AWS A5.9 / SFA-5.9</b>
G Z 18 L Nb	ER430 (mod.)

## Characteristics and typical fields of application

Solid wire of G Z 18 L Nb L / ER430 (mod.) type especially for joint welding of exhaust systems. For matching or similar materials. Stabilized with Nb to reduce tendency to grain growth. Resistant to scaling up to 900°C. Outstanding feeding characteristics and very good welding and flow characteristics.

## Base materials

1.4016 X6Cr17, 1.4511 X3CrNb17  
UNS S43000  
AISI 430

## Typical analysis


	C	Si	Mn	Cr	Nb
wt.-%	0.02	0.5	0.5	18	0.46 (≥ 12 × C)

## Mechanical properties of all-weld metal - typical values (min. values)

Condition	Hardness
u	150
s	130

u untreated, as-welded – shielding gas Ar + 2% CO<sub>2</sub>  
s heat treated, annealed – shielding gas Ar + 2% CO<sub>2</sub>, 760°C for 2 h

## Operating data

	Polarity	DC+	Dimension mm
	Shielding gas (EN ISO 14175)	M12	0.8
		M13	1.0
			1.2

Preheating as required by the base metal. Thicker matching ferritic steels can be preheated to 200 – 300°C and post weld heat treated at 700 – 750°C.

Shielding gas: Ar + 2 – 3% CO<sub>2</sub> or Ar + 1 – 2% O<sub>2</sub>

## Approvals

-