


<b>Classifications</b>						
EN ISO 18273			AWS A5.10			
S Al 4043A (AlSi5(A))			ER4043			
<b>Characteristics and typical fields of application</b>						
Solid wire for GMAW of Al alloys containing up to 2% of alloying elements and for aluminium alloys containing up to 7% Si. The weld metal is not suitable for anodizing for decorative purposes. Very fluid weld pool. Not applicable for welding hardenable alloys in high stressed zones. Thorough cleaning of the workpiece bevels is necessary prior to welding.						
<b>Base materials</b>						
EN AW-6060 [AlMgSi]	AlMgSi0,5	3.3206				
EN AW-6005A [AlSiMg(A)]	AlMgSi0,7	3.3210				
EN AW-6082 [AlSi1MgMn]	AlMgSi1	3.2315				
EN AW-6061 [AlMg1SiCu]	AlMg1SiCu	3.3211				
EN AC-45000	G-AlSi6Cu4	3.2151				
and similar.						
<b>Typical analysis of solid wire (wt.-%)</b>						
Al	Si	Fe	Cu	Mn	Mg	Zn
Bal.	4.5 – 6.0	< 0.6	< 0.3	< 0.15	< 0.2	< 0.10
<b>Mechanical properties of all-weld metal</b>						
Yield strength $R_{p0.2}$		Tensile strength $R_m$		Elongation A ( $L_0=5d_0$ )		
MPa		MPa		%		
70		130		16		
<b>Operating data</b>						
		<b>Polarity:</b> DC (+)		<b>Shielding gases:</b> (EN ISO 14175) I1, I3		<b>ø mm</b> 1.0 1.2 1.6
<b>Approvals</b>						
DB (61.132.02), CE						