

Classifications

| | |
|------------------------|-----------|
| EN ISO 18273 | AWS A5.10 |
| S Al 4047A (AISi12(A)) | ER4047 |

Characteristics and typical fields of application

Solid wire for GMAW of AISi cast alloys containing 7-12% Si. The weld metal is not suitable for anodizing for decorative purposes. Very fluid weld pool. Good mechanical properties, excellent corrosion resistance and a low melting point ensure high quality welding results. Thorough cleaning of the workpiece bevels is necessary prior to welding.

Base materials

| | | |
|----------------------------|----------------|--------|
| EN AC-42100 [AlSi7Mg0.3] | G-AlSi7Mg0.3 | 3.2371 |
| EN AC-43000 [AlSi10Mg(A)] | G-AlSi10Mg | 3.2381 |
| EN AC-43200 [AlSi10Mg(Cu)] | G-AlSi10Mg(Cu) | 3.2383 |
| EN AC-43300 [AlSi9Mg] | G-AlSi9Mg | 3.2373 |
| EN AC-44000 [AlSi11] | G-AlSi11 | 3.2211 |
| EN AC-44200 [AlSi12(A)] | G-AlSi12 | 3.2581 |
| EN AC-47000 [AlSi12(Cu)] | G-AlSi12(Cu) | 3.2583 |

and similar.


Typical analysis of solid wire (wt.-%)

| Al | Si | Fe | Cu | Mn | Mg | Zn |
|------|-------------|-------|-------|--------|-------|-------|
| Bal. | 11.0 – 13.0 | < 0.6 | < 0.3 | < 0.15 | < 0.1 | < 0.2 |

Mechanical properties of all-weld metal

| | | |
|------------------------------|---------------------------|-----------------------------|
| Yield strength $R_{p0.2}$ | Tensile strength R_m | Elongation A ($L_0=5d_0$) |
| MPa | MPa | % |
| 60 | 130 | 5 |

Operating data

| | | | |
|---|----------------------------|---|----------------------------------|
|  | Polarity: DC (+) | Shielding gases: (EN ISO 14175) I1, I3 | Ø mm 1.0 1.2 1.6 |
|---|----------------------------|---|----------------------------------|

Approvals

-